






Halogen-free, thermoplastic, highly flame retardant insulation and sheathing compound for low and medium voltage cables

<p>■ Compound class Insulation / Sheathing</p> <p>■ Standards VDE 0207 part 24 HM 2, HM 4 IEC 60092-360 SHF 1 DIN EN 50363-7 T16, T17</p>	<p>■ Compound category</p> <div style="background-color: #4CAF50; color: white; padding: 5px; text-align: center; width: 30px; margin: 0 auto;">TP</div> <p>BS 7655 section 6.1 LTS 1 - LTS 4 DIN VDE 0276-604 HM4 DIN EN 50363-8 TM7</p>	<p>■ Flame retardant ATH</p> <p>CEI 20-11 M1 VDE 0250 part 215 HM5</p>
<p>■ Typical applications</p> <p><i>Halogen-free, low smoke, thermoplastic, highly flame retardant compound for the insulation and sheathing of low and medium voltage cables in General Installation applications and shipboard.</i></p>		
 <p>Installation</p>	 <p>Shipboard</p>	
<p>■ Features</p> <div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>Flame retardant</p> </div> <div style="text-align: center;">  <p>Halogen-free</p> </div> <div style="text-align: center;">  <p>Low smoke</p> </div> </div>		

PHYSICAL PROPERTIES

Physical properties	Unit	Typical value	Test method
Density*	g/cm ³	1,49	DIN EN ISO 1183-1A
Hardness*	Shore D	52	DIN ISO 7619-1
Melt Flow Index (150°C; 21,6kg)	g/10 min	8,2	DIN EN ISO 1133

MECHANICAL PROPERTIES **

Thermoplastic	Unit	Typical value	Test method
Tensile strength	N/mm ²	10,5	IEC 811-1-1
Elongation at break	%	196	IEC 811-1-1
Tear strength	N/mm	7,6	BS 6469:99.1
After ageing in air oven 168h at 110°C	Unit	Typical value	Test method
Variation in tensile strength	%	-2,0	IEC 811-1-2
Variation in elongation at break	%	-9,7	IEC 811-1-2

THERMAL PROPERTIES **

■ Heat tests	Unit	Typical value	Test method
Hot pressure test: Penetration 6h at 90°C	%	32	DIN VDE 0472-609

RESISTANCE **

■ IRM 902 4h at 70°C	Unit	Typical value	Test method
Variation in tensile strength	%	-6,1	IEC 811-2-1
Variation in elongation at break	%	6,4	IEC 811-2-1
Variation in weight	%	6,0	IEC 811-2-1
■ Water purified 168h at 70°C	Unit	Typical value	Test method
Variation in tensile strength	%	-8,4	IEC 811-2-1
Variation in elongation at break	%	-26,7	IEC 811-2-1
Variation in weight	%	1,0	IEC 811-2-1

BURNING PROPERTIES *

■ Main burning properties	Unit	Typical value	Test method
LOI *	%	38	ASTM D 2863 A
■ Acid gas emission	Unit	Typical value	Test method
Corrosivity: pH (min.)	-	≥ 4,5	DIN VDE 0472- 813
Conductivity (max.)	μS/mm	≤ 10	

* pressed plaques, 155°C / 5 min.

** extruded tapes

PROCESSING GUIDE

■ **Extruder Type**

Standard extruders for elastomeric or thermoplastic processing

■ **Screw configuration**


Low compression screw with L/D of 20 to 25 and compression ratio of 1:1.2

■ **Tooling**

For insulation pressure tools, for jacketing tube tools are recommended.
Note: Pressure Tooling may have an effect on low temperature flexibility.

■ **Temperature profile extruder**

The profile shown below may vary slightly depending on extruder type, head design & output.



■ **Maximum mass temperature**

165 – 175°C

■ **Drying**

Not necessary if the compound has been stored in original packing under cool (max. 30°C) and dry conditions. Mecoline compounds used from open packing require pre-drying during 4–6 hours at 60–70°C.

STORAGE INFORMATION

■ **Form & packaging**

Pellets in sizes 2.8mm & 5.5mm
Moisture-resistant bags (25kg) & octabins (alu-innerliner, max. 1250kg)

■ **Shelf life**

1 year after production

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.