

TOP tapes[®]

semi-conductive nylon fabric

TTO C1100W

Composition:

- Nylon fabric
- Carbon black semi – conductive impregnation

PROPERTY	TEST METHOD	VALUE	UNIT
Weight	ISO 9073/1	100±10	g/m ²
Thickness	ISO 9073/2	0.13±0.03	mm
Tensile strength	ISO 9073/3	>100	N/cm
Elongation	ISO 9073/3	≥ 15	%
Surface resistance	DIN 54345	< 1000	Ohm/□
Volume resistance	DIN 54345	< 10 ⁶	Ohm.cm

The figures shown above are typical value and should not be used as the basis of specification.